

PP-3150-MFill3

Polypropylene Compound Reinforced with Glass Fiber

Injection Grade

Technical Data Sheet

Product Description

PP-3150-MFill3 is Co-polymer Polypropylene based Compound in natural color reinforced with 30% of Chopped Glass Fiber. This grade has good mechanical properties, good impact resistance, thermal properties and dimensional stability. It is designed for use in a wide range of injection parts especially in automotive industry.

General

Material Status: Available
 Processing Method: injection molding
 Form: Pellet
 Color: Natural

Properties

Properties	Nominal Value	Test Method
Density	1.12 g/cm ³ (±0.01)	ASTM D792
MFI (230°C/ 2.16kg)	5 g/10 min (±1)	ASTM D1238
Izod Impact, Notched	13 kJ/m ² (±1)	ISO 180
Tensile Strength at Yield	65 MPa (±5)	ASTM D638
Elongation at Break	4% (±1)	ASTM D638
Elastic Modulus	3500 MPa (±200)	ASTM D638
Heat Deflection Temperature (0.45MPa)	165 °C (±5)	ASTM D648

Typical Properties: These values are not to be considered as product specifications

For more details please contact us

www.modiranpolymer.com